



# Micromechanical model of the stochastic finite element buckling reaction of a laminated composite plate with random system parameters in a temperature environment

**Chirag Sharma**, Department of Mechanical Engineering R.D. Engineering college, Ghaziabad, -201206 India. [chiragbhardwaj@gmail.com](mailto:chiragbhardwaj@gmail.com)

## Abstract

Using a micromechanical approach, this paper demonstrates how random system properties affect the buckling response of laminated composite plates in thermal environments. The framework properties, for example, thermo-material properties, fiber volume parts of separate fiber and lattice constituents and establishment boundaries are demonstrated as free arbitrary factors. The temperature field is thought to consist of uniform temperature distributions throughout the thickness and surface of the plate. The material properties of the composite are impacted by the variety of temperatures and in view of micromechanical model. The essential definition depends on higher request shear deformity plate hypothesis and general von-Karman sorts of nonlinearity. An immediate iterative based C0 nonlinear limited component strategy related mean focused first request irritation method is out lined and tackled the stochastic direct summed up eigen esteem issue. The created stochastic method is conveniently utilized for thermally prompted issue in light of micromechanical approach with a sensible exactness. The mean and variance of plate frequency are examined through parametric studies to determine the effects of volume fractions, amplitude ratios, temperature increments, temperature distributions, geometric parameters, lay-ups, boundary conditions, and foundation parameters. The present framed approach has been approved with those accessible outcomes in written works and autonomous Monte-Carlo reenactment.

**Keywords:** Thermal buckling; random material properties; stochastic finite element; perturbation technique

## INTRODUCTION

Laminated composite plates are increasingly used as critical structural members in aerospace and many other applications due to gaining wide popularity as light weight components, ability to tailor structural properties through appropriate lamination scheme for achieving high strength and stiffness to weight ratio and durability and corrosion resistant characteristics combined with low density, make it more attractive compared to conventional materials.

## BUCKLING EQUATIONS FOR LAMINATED PLATES

A plate buckles when the in-plane load gets so large that the originally flat equilibrium state is no longer stable and the plate deflects into a non flat configuration. The load at which the departure from flat state takes place is called the buckling load. Analysis of plates buckling under in-plane loading involves solution of eigenvalue problem as opposed to the boundary value problem of equilibrium analysis. The distinctions between boundary value problems and eigenvalue problems are too involved to treat here. Instead, the buckling differential equations governing the buckling behavior from a membrane prebuckled state (prebuckling deformations are ignored) are,

$$\delta N_{x,x} + \delta N_{x,y} = 0 \quad (1)$$

$$\delta N_{xy,x} + \delta N_{y,y} = 0 \quad (2)$$

$$\delta M_{x,xx} + 2\delta M_{xy,yy} + \delta M_{x,x} + \delta N_{y,y} + N_x \delta w_{,xx} + 2N_{xy} \delta w_{,xy} + N_y \delta w_{,yy} = 0 \quad (3)$$

Where the  $\delta$  denotes a variation of the principal symbol from its value in the prebuckled equilibrium state. Thus the terms  $\delta N_x, \dots, \delta M_x$  are variations of forces and moments, respectively, from a membrane prebuckled equilibrium state. The term  $\delta u$  and  $\delta v$  are variations in displacement from the same flat prebuckled state. In appearance, the buckling differential equations resemble the equilibrium differential equations except for variational notation.

An important consequence of this type of problem is that the magnitude of the deformations after buckling cannot be determined without resort to large deflection considerations; i.e. the deformations are indeterminate when only Eqs are available.

The variations in force and moment resultants are

$$\begin{matrix} \delta N_x & A11 & A12 & A16 & \delta \xi_x & B11 & B11 & B11 & \delta K_x \\ \delta N_y & =A12 & A22 & A26 & \delta \xi_y & + [B12 & B22 & B26] & \delta K_y \end{matrix} \quad (4)$$

$$\begin{matrix} \delta N_{xy} & A16 & A26 & A66 & \delta \gamma_{XY} & B16 & B26 & B66 & \delta K_{XY} \\ \delta M_x & B11 & B12 & B16 & \delta \xi_x & D11 & D12 & D16 & \delta K_x \\ \delta M_y & =B12 & B22 & B26 & \delta \xi_y & + [D12 & D22 & D26] & \delta K_y \\ \delta M_{xy} & B16 & B26 & B66 & \delta \gamma_{XY} & D16 & D26 & D66 & \delta K_{XY} \end{matrix} \quad (5)$$

Where the variations in extensional strains and changes in curvature are related to the variations in displacements by

$$\delta \xi_x = \delta u_{,x}, \delta \xi_y = \delta v_{,y}, \delta \gamma_{XY} = \delta u_{,y} + \delta v_{,x} \quad (6)$$

$$\delta K_x = \delta w_{,xx}, \delta K_y = -\delta w_{,yy}, \delta K_{xy} = -2\delta w_{,xy} \quad (7)$$

The boundary conditions for buckling problems are applied only to the buckling deformations since the prebuckling deformations are assumed to be a membrane state. One of the distinguishing features are homogeneous, i.e., zero. Thus during buckling, the simply supported edge and clamped edge boundary conditions are

$$\begin{matrix} SSSS1: & \delta w = 0 & \delta M_n = 0 & \delta U_n = 0 & \delta U_t = 0 \\ SSSS2: & \delta w = 0 & \delta M_n = 0 & \delta N_n = 0 & \delta U_t = 0 \\ SSSS3: & \delta w = 0 & \delta M_n = 0 & \delta U_n = 0 & \delta N_{nt} = 0 \end{matrix} \quad (8)$$

$$\begin{matrix} SSSS4: & \delta w = 0 & \delta M_n = 0 & \delta N_n = 0 & \delta N_{nt} = 0 \\ CCCC1: & & \delta w = 0 & \delta W_n = 0 & \delta U_n = 0 & \delta U_t = 0 \\ CSCS1: & \delta w = 0 & \delta W_n = 0 & \delta U_n = 0 & \delta U_t = 0 \end{matrix} \quad (9)$$

The boundary conditions could be different for each edge of plate, so the number of combinations of possible boundary conditions is enormous, as it was with equilibrium problems.

A. The displacement field becomes

The displacement vector for the modified models is

$$\{\Lambda\} = \{u \quad v \quad w \quad \theta_y \quad \theta_x \quad \psi_y \quad \psi_x\}^T \quad (10)$$

Strain-displacements relations with von Karmantype geometric nonlinear elasticity are expressed as:

$$\begin{aligned}
\varepsilon_{xx} &= \varepsilon_1 \equiv \bar{u}_{,x} + \varepsilon_1^0 + z(k_1^0 + z^2 k_1^2) + \frac{1}{2} w_{,xx}^2 \\
\varepsilon_{yy} &= \varepsilon_2 \equiv \bar{v}_{,y} + \varepsilon_2^0 + z(k_2^0 + z^2 k_2^2) + \frac{1}{2} w_{,yy}^2 \\
\gamma_{xy} &= \varepsilon_6 \equiv \bar{u}_{,y} + \bar{v}_{,x} + \varepsilon_6^0 + z(k_6^0 + z^2 k_6^2) + \bar{w}_{,xy} + \bar{w}_{,yx} \\
\gamma_{yz} &= \varepsilon_4 \equiv \bar{v}_{,z} + \bar{w}_{,y} = \varepsilon_4^0 + z^2 k_4^2 \\
\gamma_{zx} &= \varepsilon_5 \equiv \bar{u}_{,z} + \bar{w}_{,x} = \varepsilon_5^0 + z^2 k_5^2
\end{aligned} \tag{11}$$

Where

$$\begin{aligned}
\varepsilon_1^0 &= u_{,xx} & k_1^0 &= \psi_{,xy} & k_1^2 &= -4/3h^2(\psi_{,xy} + w_{,xx}) \\
\varepsilon_2^0 &= v_{,yy} & k_2^0 &= \psi_{,yx} & k_2^2 &= -4/3h^2(\psi_{,yx} + w_{,yy}) \\
\varepsilon_6^0 &= u_{,y} + v_{,x} & k_6^0 &= \psi_{,xy} + \psi_{,yx} & k_6^2 &= -4/3h^2(\psi_{,xy} + \psi_{,yx} + 2w_{,xy}) \\
\varepsilon_4^0 &= \psi_{,y} + w_{,yz} & k_4^2 &= -4/h^2(\psi_{,x} + w_{,y}) \\
\varepsilon_5^0 &= \psi_{,x} + w_{,zx} & k_5^2 &= -4/h^2(\psi_{,x} + w_{,x})
\end{aligned}$$

Where, comma (,) denotes the partial differential. The mid plane strain vector  $\{\varepsilon\}$  for the model is

$$\{\varepsilon\} = (\varepsilon_1^0 \quad \varepsilon_2^0 \quad \varepsilon_6^0 \quad \varepsilon_4^0 \quad \varepsilon_5^0 \quad k_1^2 \quad k_2^2 \quad k_6^2 \quad k_4^2 \quad k_5^2)^T \tag{12}$$

The constitutive law thermal elasticity for the materials under consideration relates the stresses with strains in a plane stress state for the kth lamina oriented as an arbitrary angle with respect to the reference axis for an orthotropic layer is given by (Reddy 1997; Robert 1975)

$$\begin{aligned}
\{\sigma\}_k &= [\bar{Q}]_k \{\varepsilon\}_k \text{ or} \\
\begin{bmatrix} \sigma_{xx} \\ \sigma_{yy} \\ \sigma_{xy} \\ \sigma_{yz} \\ \sigma_{zx} \end{bmatrix} &= \begin{bmatrix} \bar{Q}_{11} & \bar{Q}_{12} & \bar{Q}_{16} & 0 & 0 \\ \bar{Q}_{12} & \bar{Q}_{22} & \bar{Q}_{26} & 0 & 0 \\ \bar{Q}_{16} & \bar{Q}_{26} & \bar{Q}_{66} & 0 & 0 \\ 0 & 0 & 0 & \bar{Q}_{44} & \bar{Q}_{45} \\ 0 & 0 & 0 & \bar{Q}_{45} & \bar{Q}_{55} \end{bmatrix} \begin{bmatrix} \varepsilon_{xx} - \alpha_{xx} \Delta T \\ \varepsilon_{yy} - \alpha_{yy} \Delta T \\ \varepsilon_{xy} \\ \varepsilon_{yz} \\ \varepsilon_{zx} \end{bmatrix} \tag{13}
\end{aligned}$$

Where  $[\bar{Q}]_k$ ,  $\{\sigma\}_k$  and  $\{\varepsilon\}_k$  are transformed stiffness matrix, stress and strain vectors of the kth lamina, respectively and  $(\alpha_x, \alpha_y)$  are the thermal expansion coefficients along x, y, z, direction,  $(\alpha_{xy}, \beta_{xy})$  are shear coefficients in x,y plane respectively. This can be obtained from the thermal coefficients in the longitudinal  $(\alpha_1, \beta_1)$  and transverse  $(\alpha_2, \beta_2)$  directions of the fibres using transformation matrix. T (X, Y, Z) is the uniform

temperature and moisture field distribution. Substituting Eq. (12) into Eq. (13) and integrating through thickness gives a relationship between stress resultants and mid-plane strain are given as Reddy [1997].

$$\begin{Bmatrix} N \\ M_i \end{Bmatrix} = \begin{bmatrix} A & B & E \\ B_{ij} & D_{ij} & F_{ij} \end{bmatrix} \begin{Bmatrix} \varepsilon^0 \\ k^0 \\ M^T \end{Bmatrix} \quad (i, j=1, 2, 6) \quad (14)$$

$$\begin{Bmatrix} Q \\ \{^2\} \\ Q \\ \{^1\} \end{Bmatrix} = \begin{bmatrix} A & D_{4j} \\ A_{4j} & D_{4j} \\ A & D & k^2 \\ A_{5j} & D_{5j} & k^2 \end{bmatrix} \begin{Bmatrix} \varepsilon^0 \\ \{^j\} \\ \{^j\} \\ \{^j\} \end{Bmatrix}; \quad \begin{Bmatrix} R \\ \{^2\} \\ R \\ \{^1\} \end{Bmatrix} = \begin{bmatrix} D & F \\ D_{4j} & F_{4j} \\ D & F & k^2 \\ D_{5j} & F_{5j} & k^2 \end{bmatrix} \begin{Bmatrix} \varepsilon^0 \\ \{^j\} \\ \{^j\} \\ \{^j\} \end{Bmatrix} \quad (j=4, 5) \quad (15)$$

$$\{N\} = \begin{bmatrix} N \\ N \\ N \end{bmatrix}^T, \{M\} = \begin{bmatrix} M \\ M \\ M \end{bmatrix}^T \& \{P\} = \begin{bmatrix} P \\ P \\ P \end{bmatrix}^T \quad (16)$$

Expressed in terms of mid plane strains and curvatures (Robert 1975; Bhagwan et al.1990). The thermal stress and moments results per unit length due to temperature change are calculated

### B. Micromechanical Approach

The material properties of the fibre composite at different temperature are evaluated using micromechanical model. Since the effect of temperature is dominant in matrix material. The degradation of the fibre composite material properties is estimated by degrading the matrix property only. The matrix mechanical property retention ratio is expressed as Upadhyay et al. (2010).The elastic constants are obtained from the following equations Upadhyay et al. (2010).

$$E_{11} = E_{f1}V_f + F_m E_m V_m \quad (17)$$

$$E_{22} = (1 - \sqrt{V_f}) F_m E_m + \frac{F_m E_m \sqrt{V_f}}{1 - \sqrt{V_f} \left(1 - \frac{F_m E_m}{E_{f2}}\right)} \quad (18)$$

$$G_{12} = (1 - \sqrt{V_f}) F_m G_m + \frac{F_m G_m \sqrt{V_f}}{1 - \sqrt{V_f} \left(1 - \frac{F_m G_m}{G_{f12}}\right)} \quad (19)$$

$$v_{12} = v_{f12}V_f + v_m V_m \quad (20)$$

Where “V” is the volume fraction and subscripts “f” and “m” are used for fibre and matrix, respectively. The effect of increased temperature on the coefficients of thermal expansion ( $\alpha$ ) is opposite from the corresponding effect on strength and stiffness. The matrix thermal property

$$F_h = \frac{1}{F_m}$$

Coefficients of thermal expansion are expressed as Upadhyay et al. (2010).

$$\alpha_{11} = \frac{E_{f1}V_f\alpha_{f1} + F_mE_mV_mF_h\alpha_m}{E_{f1}V_f + F_mE_mV_m} \quad (21)$$

$$\alpha_{22} = (1+\nu_{f12})V_f\alpha_{f2} + (1+\nu_m)V_mF_h\alpha_m - \nu_{12}\alpha_{11}$$

The elastic constants are obtained from the following equations Shen, Hui-Shen.(2001).

$$E_{11} = VfEf + VmEm \quad (22)$$

$$\frac{1}{E_{22}} = \frac{Vf}{Ef} + \frac{Vm}{Em} - \frac{Vf^2}{VfEf + VmEm} \frac{Em}{Ef} + \nu_m^2 \frac{Ef}{Em} - 2\nu_{fm} \quad (23)$$

$$\frac{1}{G_{12}} = \frac{Vf}{Ef} + \frac{Vm}{Gm} \quad (24)$$

$$\nu_{12} = Vf\nu_f + Vm\nu_m \quad (25)$$

Where "V" is the volume fraction and subscripts "f" and "m" are used for fibre and matrix, respectively. The effect of increased temperature and moisture concentration on the coefficients of thermal expansion ( $\alpha$ ) is opposite from the corresponding effect on strength and stiffness.

Coefficients of thermal expansion are expressed as Shen, Hui-Shen.(2001).

$$\alpha_{11} = \frac{VfEf\alpha_f + VmEm\alpha_m}{VfEf + VmEm} \quad (26)$$

$$\alpha_{22} = (1+\nu_f)Vf\alpha_f + (1+\nu_m)Vm\alpha_m - \nu_{12}\alpha_{11} \quad (27)$$

Other constants are related as Shen, Hui-Shen.(2001).

$\nu_{12} = Vf\nu_f + Vm\nu_m$  &  $Vm\nu_f = 1$

### C. Perturbation Technique

In general, without any loss of generality any arbitrary random variable can be represented as the sum of its mean and zero mean random part, denoted by superscripts „d“ and „r“, respectively (Singh et al. 2002).

$$K = K^d + K^r, \quad K_g = K_g^d + K_g^r, \quad \lambda_i = \lambda_i^d + \lambda_i^r, \quad q = q^d + q^r \quad (28)$$

By substituting Eq. (27) in Eq. (28) and expanding the random parts in Taylor's series keeping the first order terms and neglecting the second and higher order terms, collecting same order of the magnitude term, one obtains as (Yamin et al. 1996; Lin 1967).

$$1) \text{ Zeroth order} \quad [K^d] \{q^d\} = \lambda^d [K^d] \{q^d\} \quad (29)$$

$$2) \text{ First order} \quad [K^d] \{q^d\} + [K^r] \{q^r\} = \lambda^d [K^r] \{q^d\} + \lambda^r [K^d] \{q^r\} \quad (30)$$

Eq. (29) is the deterministic equation relating to the mean eigenvalues and corresponding mean eigenvectors, which can be determined by conventional Eigen solution procedures. Eq. (30) is the random equation, defining the stochastic nature of the thermal buckling which cannot be solved using conventional method. For this a further analysis is required.

## RESULTS AND DISCUSSION

The stochastic finite element analysis has been applied to obtain the mean and dispersion considering different random parameters of the thermal buckling load of laminated composite plate of graphite epoxy material. Fig.2. The lamina coefficients of thermal expansion including geometric and material properties are modelled as basic random variables RVs. The mean and standard deviation of the thermal buckling load are obtained considering the all random material input variables and thermal expansion coefficients as well as plate thickness taking separately as basic random variables (RVs) as stated earlier. However, the results are only presented taking SD/mean of the system property equal to 0.10 (Liu et al.1986), as the nature of the SD (Standard deviation) variation is linear and passing through the origin. Hence, the presented results would be sufficient to extrapolate the results for other COV value keeping in mind the limitation of FOPT (Klieber et al.1992). The thickness of all the lamina is assumed to be constant and of same material without varying individual property of materials used. The results obtained have been compared with MCS and those available in the literature. For the present study a nine noded serendipity element, which results in 63 degree of freedom (DOFs) per element modified form HSDT based  $C^0$  finite element model has been used for discretizing the laminate. Based on convergence, a (4x4) mesh has been used throughout for evaluation of the results. Results have been computed by employing the full (3x3) integration rule for bending stiffness matrices, thermal load vector and the geometric stiffness matrices and the reduced (2x2) integration rule for computing the shear stiffness matrices to avoid shear locking in the thin plates. The boundary conditions for the plate are as shown in Fig. 3.

A. All edges simply supported (SSSS (S1))

$$u = w = \theta_y = \psi_x = 0, \text{ at } x = 0, a; \quad v = w = \theta_x = \psi_y = 0 \text{ at } y = 0, b;$$

B. All edges simply supported (SSSS (S2))

$$v = w = \theta_y = \psi_y = 0, \text{ at } x = 0, a; \quad u = w = \theta_x = \psi_x = 0 \text{ at } y = 0, b;$$

C. All edges clamped (CCCC)

$$u = v = w = \psi_x = \psi_y = \theta_x = \theta_y = 0, \text{ at } x = 0, a \text{ and } y = 0, b;$$

The plate geometry used is characterized by aspect ratios (a/b) = 1 and 2, side to thickness ratios (a/h) = 10, 30, 80 and 100. Coefficients of thermal expansion and material constants are used for computation. We now consider a second step as the elastic constants, thermal expansion coefficients of each layers are assumed to be linear function of temperature. The only exception is the Poisson's ratio which can reasonably be assumed as constant due to weakly dependency on temperature change. For the ratio of



the SD to the mean of material and geometric properties varying from 0 to 20% with a/h= 10, 30, 80 and 100 have been considered. The thermo-elastic material properties such as  $E_{11}$ ,  $E_{22}$ ,  $G_{12}$ ,  $G_{13}$ ,  $G_{23}$ ,  $\alpha_1$ ,  $\alpha_2$ , are modelled as basic random variables (RVs). The input random variables  $b_i$  is related as  $b_1= E_{11}$ ,  $b_2=E_{22}$ ,  $b_3=G_{12}$ ,  $b_4= G_{13}$ ,  $b_5=G_{23}$ ,  $b_6=\alpha_1$ ,  $b_7=\alpha_2$ , For

the temperature dependent material properties (TD), the relation among elastic constants is given as:

$$\begin{aligned} E_{111} &= E_{110} (1 + E_{111}T + E_{111}C) \\ E_{221} &= E_{220} (1 + E_{221}T + E_{221}C) \\ G_{12} &= G_{120} (1 + G_{121}T + G_{121}C) \\ G_{13} &= G_{130} (1 + G_{131}T + G_{131}C) \\ G_{23} &= G_{230} (1 + G_{231}T + G_{231}C) \\ \alpha_{11} &= \alpha_{10} (1 + \alpha_{11}T) \\ \alpha_{21} &= \alpha_{20} (1 + \alpha_{21}T) \end{aligned}$$

Where the coefficients of temperature are defined as

$$\begin{aligned} E_{111} &= -0.5 \times 10^{-3} \\ E_{221} = G_{121} = G_{131} = G_{231} &= -0.2 \times 10^{-3} \\ \alpha_{11} = \alpha_{21} &= 0.5 \times 10^{-3} \end{aligned}$$

The thermal coefficients  $\alpha_{11}$  are taken equal in magnitude for degradation of composite plate. All layers are of equal thickness for the temperature independent material properties (TID)  $E_{111}$ ,  $E_{221}$ ,  $G_{121}$ ,  $G_{131}$ ,  $G_{231}$ ,  $\alpha_{11}$ ,  $\alpha_{21}$  quantities are taken equal to zero. For validation purposes the analysis of Tables 1(a), 1(b) and 1(c) is presented. Tables from 2 to 6 are for generation of results for various combinations. To establish the validity of the present study, the results are compared with the existing results those available in the literature.

#### D. Validation Study; Mean and Standard Deviations

In order to validate the proposed outlined approach the results for the mean and standard deviation are compared with those available in the literature and an independent Monte Carlo simulation technique.

**Table 1:** Validation Study; Mean and Standard Deviations

Lay-up	Environment Conditions	Buckling Load $N_x$ (KN)					
		(Shen 2001)			Present		
		Vf= 0.5	Vf=0.6	Vf=0.7	Vf= 0.5	Vf= 0.6	Vf= 0.7
(0/90) <sub>s</sub>	0ΔT=0°C	171.36	203.90	243.28	171.21	203.81	243.99

E. Effect of plate thickness ratio(a/h) and input random variables  $b_i$  {i=1...8, 7-8, and 9 = 0.10} on the buckling loads  $N_x$  (KN) for angle ply ( $\pm 45^\circ$ )<sub>2T</sub>, square laminated composite plate,  $V_f=0.6$ ,  $T_0=25^\circ\text{C}$ , Simple Support (S2) under Environmental Conditions

Effect of plate thickness ratio(a/h) and input random variables  $b_i$  {i=1...8, 7-8, and 9 = 0.10} on the buckling loads  $N_x$  (KN) for angle ply ( $\pm 45^\circ$ )<sub>2T</sub>, square laminated composite plate,  $V_f=0.6$ ,  $T_0=25^\circ\text{C}$ , Simple Support (S2) under Environmental Conditions shown in table 2. It is observed that for simple support (S2) the increases in amplitude ratio decreases the mean thermal postbuckling load and COV of combined random variables increases, whereas COV of plate thickness increases. On increase in temperature the mean thermal post buckling load decreases and coefficient of variations of thermal post

buckling load also varies. It is further seen that without rise in temperature mean thermal post buckling load for simply supports significantly increases

**Table 2:** Effect of plate thickness ratio(a/h) and input random variables bi{i=1...8, 7-8, and 9 = 0.10} on the buckling loadsNx (KN) for angle ply (±45°)2T, square laminated composite plate, Vf=0.6, T0=25°C, Simple Support (S2) under Environmental Conditions

a/h	Wmax/h	ΔT=0°C,				Wmax/h	ΔT=100°C,			
		Mean (KN)	Coefficient of variation (SD/Mean)Bi				Mean (KN)	Coefficient of variation (SD/Mean)Bi		
			(i=1...8)	(i=7.-8)	(i=9)			(i=1...8)	(i=7.-8)	(i=9)
10	0.3	178.026	(0.0665)	(4.8943e-004)	(0.0187)	0.3	166.0780	(0.0592)	(0.0023)	(0.0233)
	0.6	177.806	(0.0667)	(4.9003e-004)	(0.0185)	0.6	166.8566	(0.0593)	(0.0023)	(0.0238)
	0.9	178.735	(0.0664)	(4.8784e-004)	(0.0187)	0.9	169.6873	(0.0611)	(0.0023)	(0.0236)
	Wcr	171.226				Wcr	161.5558			
30	0.3	20.0468	(0.0688)	(0.0015)	(0.0421)	0.3	19.6905	(0.0709)	(0.0067)	(0.0408)
	0.6	20.0554	(0.0689)	(0.0015)	(0.0423)	0.6	20.3595	(0.0672)	(0.0067)	(0.0364)
	0.9	32.4826	(0.0634)	(9.0411e-004)	(0.0568)	0.9	25.0384	(0.0591)	(0.0042)	(0.0425)
	Wcr	17.7045				Wcr	17.3034			
80	0.3	1.3751	(0.0787)	(0.0081)	(0.0395)	0.3	1.3746	(0.0862)	(0.0366)	(0.0390)
	0.6	1.5604	(0.0761)	(0.0071)	(0.0309)	0.6	1.4733	(0.0824)	(0.0341)	(0.0362)
	0.9	4.3655	(0.0666)	(0.0025)	(0.0545)	0.9	1.6826	(0.0774)	(0.0299)	(0.0383)
	Wcr	1.0948				Wcr	1.0869			
100	0.3	0.7237	(0.0811)	(0.0122)	(0.0323)	0.3	0.7220	(0.0330)	(0.0330)	(0.0330)
	0.6	0.9005	(0.0749)	(0.0098)	(0.0370)	0.6	0.8205	(0.0306)	(0.0306)	(0.0306)
	0.9	0.9048	(0.0731)	(0.0098)	(0.0376)	0.9	0.9039	(0.0380)	(0.0380)	(0.0380)
	Wcr	0.5693				Wcr	0.5657			

F. Validation result for random material properties

Validation result for random material properties mentioned earlier, no results are available in reported literature for normalized standard deviation for the nonlinear problems. The first order perturbation technique [FOPT] results for random response has been validated. normalized standard deviation, SD (i.e. the ratio of the standard deviation (SD) to the mean value) of thermal buckling load versus the SD to the Effects of input random variables bi, {i =1 to 9) = 0.10} on the dimensionlised mean (Wcr) and coefficient of variation (Wcr) on the hygrothermally induced buckling load Nx(KN) for perfect cross ply (00/900) s square plates, plate thickness ratio (a/h=20), fiber volume fraction (Vf =0.6), initial temperature (T0 =250C), simple support (S2) under environmental conditions. The dimensionlised mean hygrothermal buckling loads are given in brackets (KN). Wcr - Linear solution. (Micromechanical Model)

**Table 3:** Validation result for random material properties

(bi)	(TID)		(TD)	
	COV, Wcr		COV, Wcr	
	ΔT=0°C	ΔT=150° C	ΔT=0°C	ΔT=150° C
E11 (i=1)	(36.3533)0.0706	(34.7229)0.0711	(35.9363)0.0706	(32.0987)0.0712
E22 (i=2)	0.0049	9.6007e-005	0.0025	3.8160e-004



G12 (i=3)	0.0059	0.0059	0.0059	0.0062
G13 (i=4)	0.0185	0.0188	0.0185	0.0180
G23(i=5)	0.0030	0.0031	0.0030	0.0030
V12 (i=6)	0.0749	1.8699e-004	0.0038	6.9102e-004
$\alpha_{11}$ (i=7)	5.5279e-05	6.3605e-004	5.5909e-005	6.8144e-004
$\alpha_{22}$ (i=8)	0.0012	0.0074	0.0012	0.0083
h (i=9)	0.0363	0.0397	0.0361	0.0398

### G. Parametric analysis of second order statistics

Table 4 shows Effect of boundary conditions and input random variables  $b_i$  ( $i=1...9$ , 7-8, 9 and 10= 0.10) on the dimensionalised mean and dispersion (SD/mean) of thermal buckling load of cross ply  $[0^0/90^0]_{2T}$  square laminated plate ( $a/h=30$ ),  $V_f=0.6$ ,  $T_0=25^{\circ}\text{C}$  subjected to uniform (U.T.) temperature and moisture distribution, in-plane uni-axial compression under  $\Delta T=0^{\circ}\text{C}$ ,  $\Delta C=0.00$  and  $\Delta T=200^{\circ}\text{C}$ . It is observed that on change of boundary conditions the expected mean thermal load changes significantly for plates with clamp (CCCC) support without rise in temperature and moisture condition. On change of environmental conditions the mean thermal load decreases, however there is small change of coefficient of variations of thermal load

**Table 4:** Validation result for random material properties

(b <sub>i</sub> )	(TID)		(TD)	
	COV, $\sigma_{cr}$		COV, $\sigma_{cr}$	
	$\Delta T=0^{\circ}\text{C}$	$\Delta T=150^{\circ}\text{C}$	$\Delta T=0^{\circ}\text{C}$	$\Delta T=150^{\circ}\text{C}$
E11 (i=1)	(36.3533) 0.0706	(34.7229) 0.0711	(35.9363) 0.0706	(32.0987) 0.0712
E22 (i=2)	0.0049	9.6007e-005	0.0025	3.8160e-004
G12 (i=3)	0.0059	0.0059	0.0059	0.0062
G13 (i=4)	0.0185	0.0188	0.0185	0.0180
G23 (i=5)	0.0030	0.0031	0.0030	0.0030
V12 (i=6)	0.0749	1.8699e-004	0.0038	6.9102e-004
$\alpha_{11}$ (i=7)	5.5279e-05	6.3605e-004	5.5909e-005	6.8144e-004
$\alpha_{22}$ (i=8)	0.0012	0.0074	0.0012	0.0083
h (i=9)	0.0363	0.0397	0.0361	0.0398

## CONCLUSIONS

The stochastic SFEM procedure outlined in the present study has been used to obtain the expected mean and coefficient of variation of the buckling load of the laminated composite plates subjected to uniform temperature rise with random system parameters. The followings are outcome of this limited study:

- 1) For various input random variables, environmental conditions for cross ply laminate, the increase in temperature effects significantly as the buckling load decreases. The effects are more prominent for temperature.
- 2) The combined effects of boundary conditions and random variables in thermal environment are studied; the plate is significantly affected by the thermal buckling load for clamp support conditions.
- 3) In general, the thermal effects are of due importance for analyzing the structure made of composite materials. The negligence of thermal effects in analyzing the system

behavior may leave the design unsafe for manufacturing and may prone to failure for reliable operational requirements.

4) The CCC plate at slightly higher temperature compared to other supports. The buckling is more dominant in plates of temperature dependent material properties as compared to temperature independent case.

5) The thick plate are less affected by random input variables and other input variables compared to thinplates.

## **FUTURE SCOPE**

There is a wide scope to extend the present study. Some of the possible extensions are:

- The present study can be extended for other geometries like cylindrical, spherical, and conical.
- The present study can be extended to various shapes of cut-outs.
- The study can be extended to include smart layers in the laminated composite plates.
- The study can be extended to functionally graded materials.
- In the present study we have used direct iterative method to handle geometric nonlinearity in the plate and elastic foundation. A more systematic approach may be used to handle the nonlinearity.
- Hygrothermal effects on laminated plate and shell.

## **REFERENCES**

1. Shen et al.[1] Thermo-mechanical postbuckling analysis of imperfect laminated plates of softening nonlinear elastic foundations.
2. Khdeir et al. [2] Thermal buckling of cross-ply laminated composite beams.
3. Shen et al. [3] Postbuckling response and failure of symmetric laminates under uniform temperature rise.
4. V. SitaThankam et al. [4] Thermal post-buckling behavior of laminated plates using a shear-flexible element based on coupled-displacement field.
5. Shen et al. [3] Postbuckling response and failure of symmetric laminates under uniform temperature rise.
6. V. SitaThankam et al. [4] Thermal post-buckling behavior of laminated plates using a shear-flexible element based on coupled-displacement field.
- H. S Shen et al. [5] Thermal post-buckling behavior of imperfect shear deformable laminate plates with temperature-dependent properties.
7. Robert M. Jones [6] Thermal buckling of uniformly heated unidirectional and symmetric cross-ply laminated fiber-reinforced composite uni-axial in-plane restrained simply supported rectangular plates.
8. Ramesh Pandey et al. [7], Hygrothermoelastic postbuckling response of laminated composite plate.
9. K. K Shukla and Y. Nath [8] Analytical solution for buckling and post-buckling of angle-ply laminated plates under thermomechanical loading.
- I. S Shen and F. W. Willians [9] Thermal postbuckling analysis of imperfect laminated plates on softening non-linear elastic foundations.
10. H. S Shen [10] Thermomechanical postbuckling analysis of imperfect laminated plates using a higher order shear-deformation theory.
11. M. Shariyat [11] Thermal buckling analysis of rectangular composite plates with temperature- dependent properties based on a layerwise theory.
12. Humayun R.H Kabir et al [12] Thermal buckling response of all-edge clamped rectangular plates with symmetric angle-ply lamination.

13. H. S Shen [13] Hygrothermal effects on postbuckling of shear deformable laminated plates.
14. A Lal et al. [14] Effect of random system properties on thermal buckling analysis of laminated composite plates.
15. **Dharamveer, Samsheer, Singh DB, Singh AK, Kumar N.** Solar Distiller Unit Loaded with Nanofluid-A Short Review. 2019;241-247. Lecture Notes in Mechanical Engineering, Advances in Interdisciplinary Engineering Springer Singapore. [https://doi.org/10.1007/978-981-13-6577-5\\_24](https://doi.org/10.1007/978-981-13-6577-5_24).
16. **Dharamveer, Samsheer.** Comparative analyses energy matrices and environmental economics for active and passive solar still. materialstoday:proceedings. 2020. <https://doi.org/10.1016/j.matpr.2020.10.001>.